

AHMEDABAD TEXTILE INDUSTRY'S RESEARCH ASSOCIATION



Cert. No. : T-854 & T-855

P.O. Ambawadi Vistar, Ahmedabad-380 015. India.
Phone : (079) 26307921-7922-7923-5132 Fax : (079)26305131-2874-1969
E-mail : pts@atira-rnd-tex.org Website : www.atira-rnd-tex.org



ATIRA PHYSICAL TESTING LABORATORY

ISO/IEC 17025 : 2005 NABL ACCREDITED

અહમદાબાદ વસ્ત્ર ઉદ્યોગ અનુસંધાન સંસ્થાન

પી.ઓ. આંબાવાડી વિસ્તાર, અહમદાબાદ-380 015 ભારત

TEST REPORT

Format No. : 06/18/02


Test Report No: A/P/1692 2009-10	Date: 11 th September, 2009
Name and address of Customer:	Pasand Exports Pvt. Ltd 201/Narayan Complex Opp Havemore Restaurant Navarangpura, Ahmedabad
Sample forwarding Letter No. & Date:	Nil dated 10-09-09
Date of receipt of Sample:	10 th September, 2009
Lab sample No. :	TT- 2275

Number of Samples : 1
Date of Performance of test(s): 11 th September, 2009
Sample Particulars: Fibre Sample

Sr. No	Sample Code & Particular	HIGH VOLUME INSTRUMENT (HVI Mode Testing) (ASTM D 5867-05)						Fibre Colour grade		
		Fibre Fineness (Mic)	MI	Upper half mean Length (mm)	UI%	SFI	Fibre Strength (g/tex) 1/8"	Rd	+b	C.G.
1.	Organic Cotton (Type Sample)	4.25	0.86	30.72	84.1	7.2	32.5	76.9	9.3	21-4

Remark :

UI - Uniformity Index, SFI - Short Fibre Index, Rd - Reflectance, +b-Yellowness, C.G. -Color Grade


SEEMA PATEL
IN-CHARGE
Signature & Seal of the Laboratory In-Charge
ATIRA, AHMEDABAD.

Page 2 of 2

★★ ISO : 17025 Accredited Laboratories ★★

Samples are not drawn by ATIRA. Result relates to the samples tested.
The report shall not be reproduced except in full, without the written approval of the laboratory.
The report is strictly confidential and for technical information of client only. Not for Advertisement, Promotion, Publicity or Litigation.
Please write Test Report number and date for all future correspondence.

Sample conditioned and tested at temp. of 27± 2° C (instead of 20/21 ± 2/1° C) and 65 ± 2% RH wherever ISO / ASTM / AATCC test methods adopted

GOOD BUSINESSES ARE MEMBERS OF ATIRA : ATIRA MEMBERSHIP IS GOOD BUSINESS